





ARIES GROUP

Products	1% on Retanned	2% on Full Chrome	4% on Crust	Solubility GM/LIT 60° C	Penetration	Light	Fastness To					
							Perspiration			Washing		
							CS	SC	SW	CS	SC	SW
ACID YELLOW 110				40	3-4	5-6	3-4	3-4	4-5	4	4-5	3-4
ACID YELLOW 42				40	3-4	4-5	3	4-5	3	1	1	3
ACID YELLOW 99				40	3-4	5-6	4	3	4	2	3	3-4
ACID YELLOW 194				40	3-4	6-7	4	2	4	2	3	3
ACID YELLOW 204				40	3-4	6-7	4	3-4	4	3-4	3-4	4
ACID YELLOW 36				40	3-4	3-4	2-3	2-3	2-3	2	2	2-3
DIRECT ORANGE 39				60	3-4	4-5	2-3	3	2	2-3	2-3	2-3
ACID ORANGE 74				40	3-4	6-7	2-3	3	4-5	3	3	4-5
ACID ORANGE 80				40	3-4	6-7	2	3	3	3	3	4
ACID ORANGE 86				40	2-3	6-7	2	2	4	3	2	4
ACID ORANGE 142				40	3-4	6-7	4	3	4	3	3	4
ACID ORANGE 56				40	4-5	5-6	3	2-3	3	3	3-4	3
ACID ORANGE 7				40	4-5	2-3	2	2	2	1	1	2

Leather Shades



Products	1% on Retanned	2% on Full Chrome	4% on Crust	Solubility GM/LIT 60° C	Penetration	Light	Fastness To					
							Perspiration			Washing		
				CS	SC	SW	CS	SC	SW	CS	SC	SW
ACID RED 357				40	2-3	6-7	2	2	4	3	3	2
ACID RED 73				40	3-4	5-6	3	2-3	2	2	2-3	2
ACID RED 97				20	4-5	4-5	1	2	3	1	1	3
ACID RED 114				40	3-4	5-6	3-4	2-3	2-3	3	3	2
DIRECT RED 239				40	3-4	3-4	3	2-3	2-3	2-3	3	3
DIRECT RED 81				40	3	3-4	2-3	2-3	1-2	2	1-2	2
ACID RED 249				40	3-4	5-6	3-4	3-4	3	3	3	3
ACID RED 131				40	3-4	4-5	3-4	3-4	3	3	3-4	3
ACID RED 119				40	2-3	5-6	3	2-3	2-3	2	3	2
ACID VIOLET 90				40	3-4	6-7	3-4	3-4	3-4	3-4	4	3
ACID VIOLET 54				40	3-4	6-7	3-4	4	3-4	3-4	3	4
ACID VIOLET 17				30	2-3	5-6	2-3	1-2	1-2	2	1	2
ACID BLUE 15				30	3	4-5	2-3	3	3	3	3	3-4



ARIES GROUP

Products	1% on Retanned	2% on Full Chrome	4% on Crust	Solubility GM/LIT 60° C	Penetration	Light	Fastness To					
							Perspiration			Washing		
							CS	SC	SW	CS	SC	SW
ACID BLUE 158				40	3-4	6-7	3	3	2-3	3-4	2-3	3
ACID BLUE 193				40	2-3	6-7	3-4	4	2-3	3	3	3
ACID BLUE 113				40	3-4	5-6	2	1-2	3	1	1	1-2
ACID BLUE 7				40	3	4-5	2-3	3	3	2-3	2	2-3
ACID GREEN 1				40	3	5-6	2-3	2	3	2-3	2	2
ACID GREEN 16				40	4-5	4-5	2-3	3	2	2-3	2	3
ACID GREEN 104				40	3-4	6-7	3-4	3	3-4	3-4	3	3
ACID GREEN 111				40	3-4	6	3	3-4	4	3-4	3	3-4
ACID GREEN 73				40	2-3	6-7	2-3	2-3	3	3	2-	3
ACID GREEN 20				40	2-3	6-7	2-3	2-3	3	3	2-3	3
ACID GREEN 68				100	4-5	6	2-3	3	3	2-3	3	2-3
ACID BROWN 188				40	4-5	4-5	2-3	3	3	3	2-3	2-3
ACID BROWN 106				40	5	5	2-3	3-4	3-4	3	2-3	2-3

Leather Shades

Products	1% on Retanned	2% on Full Chrome	4% on Crust	Solubility GM/LIT 60° C	Penetration	Light	Fastness To					
							Perspiration			Washing		
							CS	SC	SW	CS	SC	SW
ACID BROWN 422				40	3	6-7	3	3-4	3	2-3	3	2-3
ACID BROWN 83				40	4-5	6-7	1-2	3	2	2	2	3
ACID BROWN 161				40	3-4	6-7	3-4	3	2-3	3	2-3	3
ACID BROWN 425				40	4	6-7	3-4	3	3	2-3	2	2-3
ACID BROWN 432				40	3-4	6-7	3-4	2-3	3	3	3	2-3
ACID BROWN 97				40	3-4	6-7	2-3	2-3	3	2-3	3	3
ACID BROWN 85				40	3	5-6	2-3	2	2	3-4	3	3
ACID BROWN 14				40	4-5	4-5	1-2	2	2	1	1-2	2
ACID BROWN 165				40	3	6-7	3	2-3	2	2-3	3	2-3
ACID BROWN 98				40	3	6-7	3	3	3	3	3	2-3
ACID BROWN 322				40	3-4	6-7	3	3	3	3-4	2-3	3
ACID BROWN 369				40	2-3	6-7	3-4	3	3	3	3	3-4
ACID BROWN 414				40	3	5-6	2-3	3	3	2-3	3	2-3



ARIES GROUP

Products	1% on Retanned	2% on Full Chrome	4% on Crust	Solubility GM/LIT 60° C	Penetration	Light	Fastness To					
							Perspiration			Washing		
							CS	SC	SW	CS	SC	SW
ACID BROWN 452				40	3-4	6-7	3-4	3	3-4	3	2-3	3
ACID BROWN 349				40	3-4	5-6	3	2-3	2-3	3	3	2-3
ACID BROWN 434				40	3	6-7	2-3	3	2-3	2-3	2-3	2-3
ACID BROWN 360				40	3-4	4-5	3	2-3	3	2-3	3	2-3
ACID BROWN 235				40	3	5-6	3	2-3	3	2-3	3	2-3
ACID BROWN 58				40	3-4	5-6	2-3	3	2-3	3	3	3
ACID BROWN 75				40	3-4	6	3-4	3	2-3	2-3	3	3
ACID BROWN 348				40	3-4	5-6	2-3	2-3	3	2-3	3	3
ACID BROWN 354				40	3-4	5-6	3	3-4	3	2-3	2-3	2-3
ACID BROWN 355				40	2-3	6-7	3-4	3-4	3	3	3-4	3-4
ACID BROWN 365				40	3-4	6-7	3	2-3	3	3	3	3
ACID BROWN 402				40	2-3	6-7	3	3	2-3	2-3	3	2-3
ACID BROWN 282				40	2-3	6-7	3	2	2-3	2-3	3	3

Leather Shades

Products	1% on Retanned	2% on Full Chrome	4% on Crust	Solubility GM/LIT 60° C	Penetration	Light	Fastness To					
							Perspiration			Washing		
							CS	SC	SW	CS	SC	SW
ACID BLACK 84				40	2-3	6-7	3-4	3	3	2-3	3	2-3
DIRECT BLACK 170				40	3	5-6	2-3	3	3	3	3	2-3
ACID BLACK 194				100	2-3	6-7	3-4	2-3	3	3	3-4	2-3
DIRECT BLACK 19				40	3	5-6	2-3	3	2-3	2-3	2-3	3
ACID BLACK 107				40	2-3	6-7	3	2-3	3	2-3	3	3
ACID BLACK 2				40	4-5	4-5	2-3	3	2-3	2-3	3	2-3
ACID BLACK 26				40	3-4	5-6	2-3	3	2-3	2-3	3	3
ACID BLACK 1				40	4-5	3-4	2-3	2	3	2-3	3	2-3
DIRECT BLACK 155				40	2-3	5-6	2-3	3	3	3	2	2
DIRECT BLACK 168 MAP				40	3	5-6	2-3	2-3	3	3	2	3
DIRECT BLACK 168 MPD				40	3	5-6	2	2	3	3	2	2-3
ACID BLACK 210				100	4	5-6	2-3	3	3	3	3	2-3
ACID BLACK 234				100	2-3	5-6	3	3	3	2-3	3	3-4